

EX 8330

APPLICATION INFORMATION

Do not apply below 40°F or humidities above 85 percent.

APPLICATION METHOD

Airless spray or Conventional spray.

MIXING

Mix 4 parts of Part A to 1 part of Part B.

CLEAN-UP AND THINNING

Clean up and thin with American TH 600 thinner.

SPRAY EQUIPMENT

FOR AIRLESS SPRAY

Pump Ratio ----- 30:1
Air Supply (in) ----- 100 psi
Hose Diameter (ID) ----- 1/4"
Hose Length ----- 75'
Tip Size ----- .017 - .025
Atomization Pressure ----- 2,400

FOR CONVENTIONAL SPRAY

Spray Pot Dual Regulation
Air Gauges for Pot Pressure and Atomization Air

Air Supply (in) ----- 100 psi
Material Hose (ID) ----- 1/2"
Material Hose Length ----- 25 - 50
Air Hose (ID) ----- 5/16"
Fluid Pressure (psi) ----- 50 psi
Atomization Pressure (psi) ----- 80 - 90 psi
Fluid Tip Orifice Size (in) ----- .086

SAFETY INFORMATION

WARNING! FLAMMABLE, HARMFUL IF INHALED, CAUSES IRRITATION

Keep away from sparks or flame. Vapors may cause flash fire. Use with adequate ventilation. Do not breathe vapors or spray mist. Wear an appropriate, properly fitted respirator during and after applications unless air monitoring demonstrates vapor/mist levels are below applicable limits. Avoid contact with eyes, skin, and clothing. Wash thoroughly after handling.

SHIPPING DATA

Proper Shipping Name ----- Paint Liquid
Hazard Class----- Flammable Liquid

Flash Pt. °F SETA ----- 56°F Part A
98°F Part B

UN No.----- 1263

PACKAGING

<u>Shipping Wt.</u>	<u>PART A</u>	<u>PART B</u>
	Ones 9 lbs.	Quarts 2 lbs.
	Fives 46 lbs.	Gallons 8.5 lbs.

DISCLAIMER

The facts stated and the recommendations and suggestions herein are based upon experiments and supplier information believed to be reliable. No guarantee is made of their accuracy, however, and American Coatings ASSUMES NO LIABILITY FOR PRODUCT FAILURE OTHER THAN TO SUPPLY REPLACEMENT MATERIAL FOR PRODUCTS SHOWN TO BE DEFECTIVE WHEN DELIVERED OR TO REFUND THE PURCHASE PRICE. Except as stated, THERE ARE NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. AMERICAN COATINGS SHALL NOT BE LIABLE FOR SPECIAL, INCIDENTAL AND CONSEQUENTIAL DAMAGES. No statement contained herein shall be construed as an inducement to infringe existing patents or as an endorsement of specific manufacturers.